

# Fit Light Tape

## No. 738



### Environmentally considerate tape for moving and construction curing

Uses PET products such as PET bottles and clothes as raw materials

Segmented and recycled at the molecular level

Uses recycled PET fiber in the vertical threads

#### Usage

- Uses recycled PET fiber in the vertical threads of the tape.
- More than 10% reduction in CO<sub>2</sub> during incineration (compared to existing company products)
- Light-weight design, compact even for 50m rolls (similar to existing company 25m rolls). Easy to carry.
- Flexible and sticks well even on uneven surfaces.
- Can stick on polyethylene and polypropylene laminated paper and is also stackable.
- Easy to write on with oil-based ink.
- Can be removed completely with special glue.

#### Performance

Test Items	Unit	No. 738
Thickness of tape	mm	0.105
Adhesive strength	N/10mm (g/10mm)	2.2 (224.4)
Tack	Ball No.	16
Tensile strength	N/10mm (kg/10mm)	40 (4,080)
Elongation	%	25

\* The figures in the table above are measurements and are not guaranteed values.

Specifications		
Size W (mm) × L (m)	Unit packaging (rolls)	One package (rolls)
50×25	1	30
50×50	1	30

#### Base color

Semi-Clear, Blue, Green



# Cellophane Tape

## No. 252



### Strong, longtime, top seller due to high quality.

Adhesive strength, meets low temperature needs, made from polyethylene, seals containers, transparent, easy to open shrink package...because of its many high qualities, cellophane tape No. 252 gets favorable comments, and it is Sekisui's long time seller.

#### Usage

- General, light packaging
- Wrapping and fixing paper boxes
- Putting up calendars and posters

#### Performance

Test items	Unit	No. 252
Thickness of tape	mm	0.049
Thickness of base material	mm	0.034
Adhesive strength	N/10mm (g/10mm)	3.1 (316)
Tack	Ball No.	17
Unwinding force	N/10mm (g/10mm)	1.31 (133)
Holding power	mm	0.7
Tensile strength	N/10mm (K g/10mm)	36.0 (3.67)
Elongation	%	25

\* The figures in the table above are measurements and are not guaranteed values.

#### Capacity / Substrate vs. Adhesive Strength : N/10mm (g/10mm)

	0°C	23°C	40°C
Polyethylene	2.44 (249)	1.50 (153)	1.18 (120)
Polystyrene	3.54 (361)	2.71 (277)	2.48 (253)
Liner	all paper faces peeled	all paper faces peeled	paper not peeled

#### Specifications

Size W (mm) × L (m)	Unit packaging (rolls)	One package (rolls)
12×35·50·70	10	300 (200)
15×35·50·70	10	200
18×35·50·70	10	200 (150)
24×35·50·70	10	150

#### Base color

Clear

\*The figures in ( ) are standard lengths for 50m. and 70m.

\*Please feel free to consult us about other sizes.



Light packaging